

# TECHNICAL DATASHEET

## DEMPOL CSP 60

*DEMPOL CSP 60 IS AN AQUEOUS, FINE DISPERSION OF ACRYLIC / ACRYLIC ESTER COPOLYMER EMULSION*

### EMULSION PROPERTIES

Type of Polymer	: Styrene-Acrylic Acid Ester Copolymer
Solid Content (%)	: 60 ± 1
pH (at 25°C)	: 6-8.5
Average Particle Size (um) approx	: 0.29
Viscosity (Brookfield RVT-DVII+) (at 25 °C)	: < 500 mPa.s (spindle:2/20 rpm)
Stabilizing System	: Anionic
Free Monomer Content (%)	: < 0.3
Density (at 20°C)	: 1.06 - 1.08 (gr/ml)
Minimum Film Forming Temperature (°C)	: 6 ±1°C
Film Appearance (at 25°C )	: Clear, flexible,
Glass Transition Temperature (°C)	: 5

### APPLICATIONS

- Interior & Exterior Paints
- Pigmented Stuccos

### FEATURES

- Good water resistance and scrub resistance
- Good paint stability
- Clear , glossy and flexible film.
- High Solid Content
- High pigment binding capacity

## PROCESSING

---

DEMPOL CSP 60 exhibits very good compatibility with pigments and fillers and has a high pigment binding capacity.

Paints are produced in the conventional method in a high-speed impeller mill. It's recommended that the pigments and extenders are thoroughly dispersed by wetting agents (e.g. DEMPOL 0930) and dispersing agents (e.g. DEMPOL PA 40 NS) before the emulsion is added.

DEMPOL CSP 60 has a tendency to foam as all small particle dispersions. It is essential to add defoamer during the process of producing emulsion paints and similar applications.

To arrange the viscosity and processing properties of emulsion paints and pigment stuccos etc. various types of thickeners can be added. Like cellulose ethers, acrylic thickeners. (e.g. DEMPOL SA 65).

DEMPOL CSP 60 exhibits good film formation at temperatures above 6°C. It is necessary to add suitable coalescing agents (e.g. Texanol or Buthyl Diglycol Acetate) in amounts of 0.3 – 0.8 % in terms of the whole formulation.

Glycols improve the freeze-thaw stability and glossy of the finished products but do not cause any reduction of the film forming temperature.

Eventhough DEMPOL CSP 60 is protected from microorganisms. It is required to add antibacterial agents to the finished products to ensure good storage stability.

## SAFETY

---

- PERSONAL PROTECTION** : Wear suitable protective clothing , gloves and glasses for eye / face protection.
- SKIN CONTACT** : Wash skin as soon as possible with plenty of water.
- EYE CONTACT** : Flush immediately with plenty of water , keeping eyelids open , for at least 15 minutes. Remove contact lenses.  
Seek for medical assistance.

## HANDLING & STORAGE

---

**HANDLING** : Ventilate the working place thoroughly. Avoid contact with skin, eyes and clothes. No eating and drinking in the work place.

**STORAGE** : Stable for 12 months , in close drums at ambient temperature (+5 / +30°C) avoid freezing temperatures and sources of heat and direct sunlight.

## NOTE

The above information is based on our knowledge and experience. In view of many factors that may affect processing and application, these data do not relieve end-users from the responsibility of carrying out their own tests and experiments.

**DEMPOL CHEMICAL CO.LTD**

Organize Sanayi Bölgesi  
ADANA/TURKEY

Tel :00 90 535 849 89 06

Fax : 00 90 322 261 68 86

E-mail : [mdemirel01@gmail.com](mailto:mdemirel01@gmail.com)